

# CATIONIC RAPID SETTING 2 (CRS2)



## APPLICATION

It is used for penetration macadam, grouting and surface dressing

## OBJECTIVES

- Easier spray application
- Strong resistance to movement of structural layers
- Good for shoulders and freshly laid base layers

## SPECIFICATIONS

Sr. No.	Tests	Results	Specs.	Test Method
1	Residue on 600 micron, sieve test	0.016	<0.05	Annex B
2	Viscosity @ 50°C	115	100-300	IS 3117
3	Coagulation at low temperature	NIL	NIL	Annex C
4	Miscibility with water	NIL	NIL	Annex H
5	Storage stability after 24 hrs.	0.19	<1	Annex D
6	Particle Charge	+Ve	POSITIVE	Annex E
7	Percentage of residue	68.2	>67	Annex J
8	Penetration @ 25°C	90	80-150	IS 1203
9	Ductility @ 27°C	50+	>50	IS 1208
10	Solubility in trichloroethylene	99.1	>98.0	IS 1216

## PACKING

Available in Bulk, 200kg RCD Drums & 200kg HDPE drums

NB: Don't mix water with bituminous emulsions