

# ALTIS EM 2



Grease

High temperature high speed polyurea grease.

## APPLICATIONS

**Multi purpose high temperature high speed grease**  
**Sealed for life applications**

### Recommendation

- **ALTIS EM 2** is pre-eminently designed for the lubrication of electrical motor bearings.
- Also suitable for lubrication of bearings, slides, racks subjected to high temperatures in dry and mildly humid environments, bearings of electric motors, generators, bearings of extraction fans for hot gas or steam, bearings of dryers, pumps, oven conveyors, and all other applications where rotation speeds and temperatures are high.
- Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system or cartridges.

## SPECIFICATIONS

- ISO 6743-9: L-XBFEA 2
- DIN 51502: K2P -20

## ADVANTAGES

**Thermal and mechanical stability**  
**No harmful substances**  
**Outstanding long-life**

- Allows long re-lubrication intervals.
- Very good stability in application and in storage.
- Can be easily pumped and injected.
- Very good adhesion to metals.
- Excellent antirust and anticorrosion properties.
- Excellent thermal stability linked with excellent reversibility.
- **ALTIS EM 2** does not contain lead, or other heavy metals considered harmful to human health and the environment.

TYPICAL CHARACTERISTICS	METHODS	UNITS	ALTIS EM 2
Soap/thickener		-	Polyurea
NLGI grade	ASTM D 217/DIN 51 818	-	2
Color	Visual	-	Green
Appearance	Visual	-	Smooth
Operating temperature range		°C	- 20 to 160
Penetration at 25°C	ASTM D 217/DIN51 818	0.1 mm	265 - 295
Oil separation 168 hrs. at 40°C	DIN 51 817/IP 121/NFT 60-191	% mass	< 1
Bearing behavior 10.000rpm/149°C	ASTM D 3336	Hrs.	> 1300
Anti-rust performance SKF- EMCOR	DIN 51 802/IP220/NFT 60-135/ISO 11007	rating	0 - 0
Dropping point	IP 396/NFT 60 102 C	°C	> 260
Kinematic viscosity of the base oil at 40°C	ASTM D 445/DIN 51 562-1/ISO 3104/IP71	mm <sup>2</sup> /s (cSt)	110
FAG-FE9 3000/1.5/170 °C	DIN 51821	Hrs F10/F50	> 225

Above characteristics are mean values given as an information.

TOTAL LUBRIFIANTS  
Industrie & Spécialités  
17-04-2008 (supersedes 30-10-2007)  
ALTIS EM 2  
1/1



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.  
A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser [www.quick-fds.com](http://www.quick-fds.com).